

Hole ID	Zone/Deposit	From (m)	To (m)	Length (m)	Au (g/t)	UTM East	UTM North	Elevation	Azimuth °	Dip °	Hole Length (m)
<b>KBRC139</b>	Boin	1.0	17.0	<b>16.0</b>	<b>0.69</b>	518700	633234	130	120	-60	80
<b>KBRC140</b>	Boin	4.0	7.0	3.0	0.31	519121	633708	155	120	-60	80
and		13.0	14.0	1.0	0.44						
<b>KBRC141</b>	Boin	10.0	21.0	11.0	0.34	519018	633704	156	114	-50	120
and		48.0	95.0	<b>47.0</b>	<b>1.67</b>						
including		49.0	58.0	<b>9.0</b>	<b>2.96</b>						
and incl.		75.0	85.0	<b>10.0</b>	<b>3.63</b>						
<b>KBRC143</b>	Boin	3.0	17.0	14.0	0.56	519395	634172	120	114	-60	108
<b>KBRC144</b>	Boin	146.0	148.0	2.0	0.51	519378	634178	120	120	-60	150
<b>KBRC145</b>	Boin	48.0	55.0	7.0	0.54	520325	635410	117	120	-60	150
<b>KBRC146</b>	Boin	7.0	10.0	3.0	0.24	520456	635619	124	114	-50	100
and		30.0	62.0	<b>32.0</b>	<b>0.92</b>						
including		42.0	54.0	<b>12.0</b>	<b>1.78</b>						
and incl.		59.0	61.0	2.0	0.52						
<b>KBRC147</b>	Boin	50.0	59.0	9.0	0.52	520424	635582	124	114	-50	102
<b>KBRC148</b>	Boin	56.0	58.0	2.0	0.69	520391	635546	122	114	-50	108
and		75.0	77.0	2.0	0.30						
<b>KBRC149</b>	Boin	38.0	41.0	3.0	0.36	520378	635496	120	114	-50	100
<b>KBRC150</b>	Boin	59.0	94.0	35.0	0.57	520335	635517	125	114	-65	148
including		65.0	91.0	26.0	0.70						
and		130.0	135.0	5.0	0.59						
and		141.0	148.0	7.0	0.42						
<b>KBRC150A</b>	Boin	72.0	74.0	2.0	0.59	520338	635514	122	114	-65	174
and		87.0	108.0	<b>21.0</b>	<b>1.19</b>						
and		136.0	139.0	3.0	1.01						
and		145.0	162.0	17.0	0.44						

Hole ID	Zone/Deposit	From (m)	To (m)	Length (m)	Au (g/t)	UTM East	UTM North	Elevation	Azimuth °	Dip °	Hole Length (m)
<b>KBRC151</b>	Boin	9.0	20.0	<b>11.0</b>	<b>2.30</b>	519349	634402	131	120	-60	156
and		62.0	65.0	3.0	0.63						
and		136.0	144.0	8.0	0.55						

Notes for 2020 Enchi Gold Project drill results:

1. Intervals reported are core lengths with true width estimated to be 75 - 85%.
2. Length-weighted averages from uncut assays.
3. All drilling completed by independent contractor.
4. All drilling samples sealed on site and delivered directly to independent lab Intertek Mineral Limited located in Tarkwa, Ghana for preparation and 50g Fire Assay with AAS finish.
5. QA/QC procedures include industry standard inclusion of standards, blanks, and duplicates in all sample batches.
6. Results pending for holes KBRC138, KBRC142, and KBRC152 - 159